

high density polyethylene

*Test specimen from compression moulded sheet at 23°C.

* FRR values are statistical and calculated by dividing MFR values.

* Notch Impact Test specimen from compressed moulded sheet 23°C and The data quoted are average values.

Applications:

Blown and Film

NO.	Property	Value	Test Method
1	Density	0.949 g/cm ³	ISO 1183
2	Fish Eye Note	<3	Internal
3	FRR (21.6/5)	29	-
4	MFR @ 190°C/21.6kg	8.0g/10min	ISO 1133
5	MFR @ 190°C/5kg	0.28 g/10min (approx)	ISO 1133



Web: www.retrona.co

Mail: sales@retrona.co

Tell: +989962555933